

GI 115 Flex

Primer and mortar resin

- Flexible
- For critical substrates
- High capillary activity
- Total Solid according to the test method of Deutsche Bauchemie



GREMMLER®
BAUCHEMIE

Product description:	GI 115 FLEX is an unfilled and transparent curing dual-component reaction plastic based on epoxy resin.
Usage area:	<ul style="list-style-type: none">• Workshops, industrial warehouses, parking areas
Usage:	<ul style="list-style-type: none">• Primer under coating systems and floorings• Also usable as primer for outside areas• Formulation of moisture compatible filler and mortar systems
Properties:	<ul style="list-style-type: none">• Low viscosity• High capillary activity even in low temperatures• Very good adhesion on: Tiles, metallic substrates like aluminium, steel, zinc, brass etc., old coatings, a diverse amount of plastics as well as further critical substrates
Substrate:	<ul style="list-style-type: none">• Residual moisture: < 6 % cement-based substrate (tested by CM) 1 mass % weight anhydride screed.

Technical Data

Colour:	Transparent, yellowish
Pack size:	30 kg; other units on request
Storage life:	From production date 12 months; store in original containers; dry, cool, frost free
Density at 23°C / 50 % air humidity: EN ISO 2811-1:2011	Approx. 1.07 g/cm ³
Adhesive pull strength: EN 1542	> Concrete fracture
Shore hardness: ISO 7619-1:2012	D > 70
Solid parts	Approx. 100 %
Viscosity (25 °C, V03.4): EN ISO 2884-1:2006	Componente A: 200 – 350 mPas Componente B: 1200 – 1700 mPas
Mixing ratio:	2 : 1 (by weight) 1.83 : 1 (by volume)
UV-resistance:	A slight change in colour and some chalking is expected.
Chemical resistance:	When completely cured resistant against: Water, sea and wastewater, numerous brines, diluted acids, saline solutions, mineral oils, lubricants, fuels and many solvents (with some materials a change in colour is possible). We advise to carry out suitability tests in advance.

GI 115 Flex

Primer and mortar resin



Processing Data:

Material usage:	250 – 400 g/m ² as primer for even substrates (rough substrates lead to a higher usage) 300 – 500 g/m ² (for rough substrates) 1:10 – 1:25 as mortar depending on the grading curve, application and the open porosity of the finished layer. These values are dependent on how the product is processed and on the quality of the substrate. The values are therefore only for a rough estimate.
Processing time (50 % air humidity):	15 – 20 minutes (30 °C) 30 – 40 minutes (20 °C) 60 – 80 minutes (10 °C)
Revision time (50 % air humidity):	Min. 6 – 8 hours, max. 12 hours at 30 °C Min. 12 – 16 hours, max. 24 hours at 20 °C Min. 24 – 36 hours, max. 48 hours at 10 °C
Curing time (complete mechanical stress at 50 % air humidity):	3 days (30 °C) 7 days (20 °C) 10 days (10 °C)
Processing temperature:	10 – 30 °C

Processing:

Preparation of the substrate:	<ul style="list-style-type: none">• Substrate must be dry, clean, rough, stable and free of separating substances like oil, fats etc.• Must be grinded or blasted. Depending on the preparation work, the surface may be rough in some places which will influence the consumption.• Iron and Steel areas are to be prepared by removal of rust until a standard degree of purity Sa 2.5 according to DIN 55928.
Tools:	<ul style="list-style-type: none">• Rubber slider, short or medium piled roller, trowel, toothed squeegee, smoothing trowel, etc..
Mixing:	<ul style="list-style-type: none">• Pour the curing agent completely into the resin compound.• Mix intensively with slow turning mixer (we advise a double-stirrer with the stirring units turning the opposite direction to each other).• Fill into another vessel and mix again.• Before applying to the substrate make sure to have an even and smear-free mixture.
Application:	
Primer:	<ul style="list-style-type: none">• Apply the product with a rubber slider and evenly spread with short or medium piled roller in cross pattern.• If the revision time is exceeded then the recently applied and still wet area has to be broadcasted with fire-dried quartz sand in advance or otherwise this area has to be prepared after curing by grinding for the next layer.
Self-levelling filler up to 2 mm:	<ul style="list-style-type: none">• The ready-to-apply coating GI 115 Flex is to be mixed 1:1 with GREPOX SLD (20 °C, dependent on temperature).• The filler is poured onto the prepared area and evenly spread with a toothed squeegee or a smoothing trowel.
Mortar:	<ul style="list-style-type: none">• The product is poured onto the prepared area, the appropriate layer thickness is adjusted by use of metal profiles and then the coating is manually or mechanically compressed.

GI 115 Flex

Primer and mortar resin



Processing conditions:	<ul style="list-style-type: none">• For layer thicknesses > 1 cm, intermediate compression should be used to ensure sufficient adhesive strength of the mortar.
	<ul style="list-style-type: none">• The material, air and ground temperature must be between 10 °C and 30 °C during the processing, installation and curing time.
	<ul style="list-style-type: none">• The substrate temperature must be at least 3 °C above the dew point.
	<ul style="list-style-type: none">• The air humidity should not be above 80 % at any time. The application should take place when temperature is at a constant or falling value to avoid blisters because of the extension of air inside the substrate. It is important to keep an eye on the ventilation during and after the application. The area must be protected from any direct water contact during the whole curing time.

Further information:

CE-label:	DIN EN 13813: 2002
Safe Handling:	The product is intended for professional use. DGUV Rule 113-012: Handling with Epoxy resins Please note the current safety data sheets.
VOC-content:	VOC-directive 2004/42/EG: Category IIA/j type Ib < 500 g/l VOC
Disposal:	Disposal with the assistance of a disposal specialist under consideration of the current safety data sheets.
GISCODE:	RE 30

Data base:

The determination of all the data and application information is based in laboratory tests. Measured values in practice may differ because of influences beyond our control.

Legal foundation:

The following specifications as well as the recommendations for handling and use of our products are based upon our knowledge and experience under normal conditions, at proper storing and application. Because of different materials, substrates and working conditions other than given normal values, a warranty of a working result or a liability – for whatever legal relationship - cannot be justified from these instructions or a verbal guidance respectively, unless intent or gross fault can be imputed to us. Here, the user has to prove that he had transferred in written form, in time and completely every knowledge that is necessary for an appropriate and promising estimation. The user is obliged to test the products on their suitability for the intended purpose. Incidentally our respective terms and conditions of business are valid. You get these on www.gremmler.de. Only the newest edition of this technical data sheet is valid.