

# GI 116

## Water based primer

- Dispersion primer / sealing
- Water-dilutable
- Solvent free



**GREMMLER®**  
**BAUCHEMIE**

<b>Product description:</b>	GI 116 is a solvent-free, water based, unfilled and non-pigmented dual component reaction plastic based on epoxy resins.
<b>Usage area:</b>	<ul style="list-style-type: none"><li>• Workshops, industrial halls</li></ul>
<b>Usage:</b>	<ul style="list-style-type: none"><li>• Primer under water based coating systems and floorings</li><li>• Dust binding of cement-bound substrates, e.g. in workshops, industrial halls</li></ul>
<b>Properties:</b>	<ul style="list-style-type: none"><li>• Very good adhesion on: Tiles, metallic substrates like aluminium, steel, zinc, brass etc., old coatings, various plastics as well as further critical substrates</li><li>• Only for inside areas</li><li>• Diffusible</li><li>• Good abrasion resistance</li></ul>
<b>Substrate:</b>	<ul style="list-style-type: none"><li>• Residual moisture: &lt; 6 % cement-based substrate (tested by CM) 0,5 mass % weight anhydride screed.</li></ul>

## Technical Data

<b>Colour:</b>	Transparent, yellowish
<b>Pack size:</b>	30 kg; other units on request
<b>Storage life:</b>	From production date 12 months; store in original containers; dry, cool, frost free
<b>Density at 23°C / 50 % air humidity:</b> EN ISO 2811-1:2011	Approx. 1.06 g/cm <sup>3</sup>
<b>Adhesive pull strength:</b> EN 1542	> Concrete fracture
<b>Solid parts</b>	Approx. 45 %
<b>Viscosity (25 °C, V03.4):</b> EN ISO 2884-1:2006	Componente A: 240 – 360 mPas Componente B: < 100 mPas
<b>Mixing ratio:</b>	1 : 3 (by weight) 30 : 100 (by volume)
<b>UV-resistance:</b>	A slight change in colour and some chalking is expected.
<b>Chemical resistance:</b>	When completely cured resistant against: Water, sea and wastewater, numerous brines, diluted acids, saline solutions, mineral oils, lubricants, fuels and many solvents (with some materials a change in colour is possible). We advise to carry out suitability tests in advance.

# GI 116

## Water based primer



### Processing Data:

<b>Material usage:</b>	250 - 400 g/m <sup>2</sup> as primer for even substrates (rough substrates lead to a higher usage) 130 – 250 g/m <sup>2</sup> as dust binding coating dilute with 20 % water These values are dependent on how the product is processed and on the substrate. The values are only for a rough estimate.
<b>Processing time (50 % air humidity):</b>	20 – 25 minutes (30 °C) 40 – 50 minutes (20 °C) 80 – 100 minutes (10 °C) End of pot life is not visible
<b>Revision time (50 % air humidity):</b>	Min. 6 – 8 hours, max. 12 hours at 30 °C Min. 12 – 16 hours, max. 24 hours at 20 °C Min. 24 – 48 hours, max. 48 hours at 10 °C
<b>Curing time (complete mechanical stress at 50 % air humidity):</b>	3 days (30 °C) 7 days (20 °C) 10 days (10 °C)
<b>Processing temperature:</b>	10 – 30 °C

### Processing:

<b>Preparation of the substrate:</b>	<ul style="list-style-type: none"><li>• Substrate must be dry, clean, rough, stable and free of separating substances like oil, fats etc.</li><li>• Must be grinded or blasted. Depending on the preparation work, the surface may be rough in some places which will influence the consumption.</li><li>• Iron and Steel areas are to be prepared by removal of rust until a standard degree of purity Sa 2.5 according to DIN 55928.</li></ul>
<b>Tools:</b>	<ul style="list-style-type: none"><li>• Rubber slider, short or medium piled roller, trowel, toothed squeegee, smoothing trowel, etc.</li><li>• Tools to be cleaned with water, not with solvents!</li></ul>
<b>Mixing:</b>	<ul style="list-style-type: none"><li>• Pour the resin compound completely into the curing agent.</li><li>• Mix intensively with slow turning mixer (we advise a double-stirrer with the stirring units turning the opposite direction to each other).</li><li>• Fill into another vessel and mix again.</li><li>• Before applying to the substrate make sure to have an even and smear-free mixture.</li></ul>
<b>Application:</b>	<ul style="list-style-type: none"><li>• Apply the product with a rubber slider and evenly spread with short or medium piled roller in cross pattern.</li><li>• In case of bigger areas care must be taken to work on in time in order to minimize overlapping traces and colour differences.</li><li>• Within the revision time the second layer can be applied directly on the first layer.</li><li>• If the revision time is exceeded then the recently applied and still wet area has to be broadcasted with fire-dried quartz sand in advance or otherwise this area has to be prepared after curing by grinding for the next layer.</li></ul>

# GI 116

## Water based primer



---

**Processing conditions:**

- The material, air and ground temperature must be between 10 °C and 30 °C during the processing, installation and curing time.
  - The substrate temperature must be at least 3 °C above the dew point.
  - The air humidity should not be above 80 % at any time. The application should take place when temperature is at a constant or falling value to avoid blisters because of the extension of air inside the substrate. It is important to keep an eye on the ventilation during and after the application. The area must be protected from any direct water contact during the whole curing time.
- 

**Further information:**

---

<b>CE-label:</b>	DIN EN 13813: 2002
<b>Safe Handling:</b>	The product is intended for professional use. DGUV Rule 113-012: Handling with Epoxy resins Please note the current safety data sheets.
<b>VOC-content:</b>	VOC-directive 2004/42/EG: Category IIA/j type wb <140 g/l VOC
<b>Disposal:</b>	Disposal with the assistance of a disposal specialist under consideration of the current safety data sheets.
<b>GISCODE:</b>	RE 20

---

**Data base:**

The determination of all the data and application information is based in laboratory tests. Measured values in practice may differ because of influences beyond our control.

**Legal foundation:**

The following specifications as well as the recommendations for handling and use of our products are based upon our knowledge and experience under normal conditions, at proper storing and application. Because of different materials, substrates and working conditions other than given normal values, a warranty of a working result or a liability – for whatever legal relationship - cannot be justified from these instructions or a verbal guidance respectively, unless intent or gross fault can be imputed to us. Here, the user has to prove that he had transferred in written form, in time and completely every knowledge that is necessary for an appropriate and promising estimation. The user is obliged to test the products on their suitability for the intended purpose. Incidentally our respective terms and conditions of business are valid. You get these on [www.gremmler.de](http://www.gremmler.de). Only the newest edition of this technical data sheet is valid.