

# GI 217

## Plasticizer-resistant top coat

- Tough
- Glossy
- Total Solid according to the test method of Deutsche Bauchemie



**GREMMLER®**  
**BAUCHEMIE**

<b>Product description:</b>	GI 217 is an unfilled and non-pigmented dual-component reaction plastic based on an aspartic acid ester.
<b>Usage area:</b>	<ul style="list-style-type: none"><li>• Inside and outside area: car warehouses and garages</li></ul>
<b>Usage:</b>	<ul style="list-style-type: none"><li>• Topcoat for industrial and decorative floor coating systems in layer thicknesses from 0,15 mm to 0,3 mm</li></ul>
<b>Properties:</b>	<ul style="list-style-type: none"><li>• Medium mechanically and highly chemically resistant</li><li>• Resistant against plasticizers</li><li>• High abrasion and scratch resistance</li><li>• Tough</li><li>• Glossy</li><li>• Lightfast and weather resistant</li><li>• The top coat optically enhances the colours of the décor floor coatings and makes them appear many times more intensive and powerful.</li></ul>
<b>Substrate:</b>	<ul style="list-style-type: none"><li>• A recently coated area</li></ul>

### Technical Data

<b>Colour:</b>	Transparent, glossy
<b>Pack size:</b>	3 kg, 5 kg; other units on request
<b>Storage life:</b>	From production date 12 months; store in original containers; dry, cool, frost free
<b>Density at 23°C / 50 % air humidity:</b> EN ISO 2811-1:2011	Approx. 1.1 g/cm <sup>3</sup>
<b>Adhesive pull strength:</b> EN 1542	> Concrete fracture
<b>Shore hardness:</b> ISO 7619-1:2012	D > 65
<b>Solid parts</b>	Approx. 100 %
<b>Viscosity (25 °C, V03.4):</b> EN ISO 2884-1:2006	Component A: 400 – 600 mPas Component B: 380 – 590 mPas
<b>Mixing ratio:</b>	3 : 2 (by weight) 5 : 3 (by volume)
<b>UV-resistance:</b>	A slight change in colour and some chalking is expected.
<b>Chemical resistance:</b>	When completely cured resistant against: Water, sea and wastewater, numerous brines, diluted acids, saline solutions, mineral oils, lubricants, fuels and many solvents (with some materials a change in colour is possible). Not resistant to: Alcohols We advise to carry out suitability tests in advance.

# GI 217

## Plasticizer-resistant top coat



### Processing Data:

<b>Material usage:</b>	200 – 400 g/m <sup>2</sup> These values are dependent on how the product is processed and on the substrate. The values are therefore only for a rough estimate.
<b>Processing time (50 % air humidity):</b>	10 – 15 minutes (30 °C) 20 – 30 minutes (20 °C) 30 – 40 minutes (10 °C)
<b>Revision time (50 % air humidity):</b>	Min. 1 – 2 hours, max. 12 hours at 30 °C Min. 2 – 4 hours, max. 24 hours at 20 °C Min. 4 – 8 hours, max. 48 hours at 10 °C
<b>Curing time (complete mechanical stress at 50 % air humidity):</b>	3 days (30 °C) 7 days (20 °C) 10 days (10 °C)
<b>Processing temperature:</b>	10 – 30 °C

### Processing:

<b>Preparation of the substrate:</b>	<ul style="list-style-type: none"><li>• Substrate must be dry, clean, rough, stable and free of separating substances like oil, fats etc.</li><li>• The sealing must be applied within the revision time on a recently coated area.</li></ul>
<b>Tools:</b>	<ul style="list-style-type: none"><li>• Rubber slider, short or medium piled roller</li></ul>
<b>Mixing:</b>	<ul style="list-style-type: none"><li>• Pour the curing agent completely into the resin compound.</li><li>• Mix intensively with slow turning mixer (we advise a double-stirrer with the stirring units turning the opposite direction to each other).</li><li>• Fill into another vessel and mix again.</li><li>• Before applying to the substrate make sure to have an even and smear-free mixture.</li><li>• GI 217 is ready formulated and may not be filled or diluted.</li></ul>
<b>Application:</b>	<ul style="list-style-type: none"><li>• The product is poured over the prepared area, applied with a rubber slider and spread evenly in a cross shaped pattern with a short or medium oiled roller.</li><li>• In case of bigger areas care must be taken to work on in time in order to minimize overlapping traces and colour differences.</li></ul>
<b>Processing conditions:</b>	<ul style="list-style-type: none"><li>• The material, air and ground temperature must be between 10 °C and 30 °C during the processing, installation and curing time.</li><li>• The substrate temperature must be at least 3 °C above the dew point.</li><li>• The air humidity should not be above 80 % at any time. The application should take place when temperature is at a constant or falling value to avoid blisters because of the extension of air inside the substrate. It is important to keep an eye on the ventilation during and after the application. The area must be protected from any direct water contact during the whole curing time.</li></ul>

# GI 217

## Plasticizer-resistant top coat



### Further information:

<b>CE-label:</b>	DIN EN 13813: 2002
<b>Safe Handling:</b>	The product is intended for professional use. Leaflet M044, production and processing of Polyurethanes and isocyanate. Please note the current safety data sheets.
<b>VOC-Content:</b>	VOC-directive 2004/42/EG: Category IIA/j type Ib < 500 g/l VOC
<b>Disposal:</b>	Disposal with the assistance of a disposal specialist under consideration of the current safety data sheets.
<b>GISCODE:</b>	PU 40

#### Data base:

The determination of all the data and application information is based in laboratory tests. Measured values in practice may differ because of influences beyond our control.

#### Legal foundation:

The following specifications as well as the recommendations for handling and use of our products are based upon our knowledge and experience under normal conditions, at proper storing and application. Because of different materials, substrates and working conditions other than given normal values, a warranty of a working result or a liability – for whatever legal relationship - cannot be justified from these instructions or a verbal guidance respectively, unless intent or gross fault can be imputed to us. Here, the user has to prove that he had transferred in written form, in time and completely every knowledge that is necessary for an appropriate and promising estimation. The user is obliged to test the products on their suitability for the intended purpose. Incidentally our respective terms and conditions of business are valid. You get these on [www.gremmler.de](http://www.gremmler.de). Only the newest edition of this technical data sheet is valid.