

GI 219

Top coat for higher layer thicknesses

- Glossy
- Pigmented
- Total Solid according to the test method of Deutsche Bauchemie



GREMMLER®
BAUCHEMIE

Product description:	GI 219 is an unfilled and transparent curing dual-component reaction plastic based on polyurethane-resin.
Usage area:	<ul style="list-style-type: none">• Inside and outside area: e.g. balconies, terraces, pergolas and showrooms behind windows
Usage:	<ul style="list-style-type: none">• High glossy, scratch-resistant, light and weather resistant top coat with brilliance and penetration as well as high transparency for decorative flooring systems like full flakes coatings, synthetic resin screeds and stone carpets with rough surface• GI 219 is not approved for the sealing of flat and compact surfaces
Properties:	<ul style="list-style-type: none">• Medium mechanically and highly chemically resistant• Resistant against plasticizers• High abrasion and scratch resistance• Tough• Glossy• Lightfast and weather resistant• Only useable in one layer• The top coat optically enhances the colours of the décor floor coatings and makes them appear many times more intensive and powerful• Low tendency to foaming and the formation of fine bubbles in thick layers compared to standard polyurethane resin sealings
Substrate:	<ul style="list-style-type: none">• Stone carpets, synthetic resin screeds or other rougher surfaces

Technical Data

Colour:	Transparent, glossy
Pack size:	5 kg, 10 kg; other units on request
Storage life:	From production date 12 months; store in original containers; dry, cool, frost free
Density at 23°C / 50 % air humidity: EN ISO 2811-1:2011	Approx. 1.2 g/cm ³
Adhesive pull strength: EN 1542	> Concrete fracture
Shore hardness: ISO 7619-1:2012	D > 75
Solid parts	Approx. 100 %
Viscosity (25 °C, V03.4): EN ISO 2884-1:2006	Component A: 300 – 450 mPas Component B: 390 – 580 mPas
Mixing ratio:	2 : 3 (by weight) 1 : 1.65 (by volume)
UV-resistance:	A slight change in colour and some chalking is expected. Polyurethanes with this composition only have a very small chance of colour change and chalking when under influence of UV-radiation. Due to the permeability of plastics to UV-radiation it is necessary to take into account, that the light-stable coating system components need to have this property as well.

GI 219

Top coat for higher layer thicknesses



Chemical resistance:	When completely cured resistant against: Water, sea and wastewater, numerous brines, diluted acids, saline solutions, mineral oils, lubricants, fuels and many solvents (with some materials a change in colour is possible). Not resistant to: Alcohols We advise to carry out suitability tests in advance.
-----------------------------	---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

Processing Data:

Material usage:	300 – 600 g/m ² These values are dependent on how the product is processed and on the substrate. The values are therefore only for a rough estimate.
Processing time (50 % air humidity):	20 – 25 minutes (30 °C) 40 – 50 minutes (20 °C) 80 – 100 minutes (10 °C)
Curing time (complete mechanical stress at 50 % air humidity):	3 days (30 °C) 7 days (20 °C) 10 days (10 °C)
Processing temperature:	10 – 30 °C

Processing:

Preparation of the substrate:	<ul style="list-style-type: none">• Substrate must be dry, clean, rough, stable and free of separating substances like oil, fats etc.• The sealing must be applied within the revision time on a recently coated area, stone carpet or synthetic resin screeds.
Tools:	<ul style="list-style-type: none">• Rubber slider, short or medium piled roller
Mixing:	<ul style="list-style-type: none">• Pour the curing agent completely into the resin compound.• Mix intensively with slow turning mixer (we advise a double-stirrer with the stirring units turning the opposite direction to each other).• Fill into another vessel and mix again.• Before applying to the substrate make sure to have an even and smear-free mixture.• GI 219 is ready formulated and may not be filled or diluted.
Application:	<ul style="list-style-type: none">• The product is poured over the prepared area, applied with a rubber slider and spread evenly in a cross shaped pattern with a short or medium oiled roller.• In case of bigger areas care must be taken to work on in time in order to minimize overlapping traces and colour differences.
Processing conditions:	<ul style="list-style-type: none">• The material, air and ground temperature must be between 10 °C and 30 °C during the processing, installation and curing time.• The substrate temperature must be at least 3 °C above the dew point.• The air humidity should not be above 80 % at any time. The application should take place when temperature is at a constant or falling value to avoid blisters because of the extension of air inside the substrate. It is important to keep an eye on the ventilation during and after the application.

GI 219

Top coat for higher layer thicknesses



- The area must be protected from any direct water contact during the whole curing time.

Further information:

CE-label:	DIN EN 13813: 2002 DIN EN 1504-2: 2004
Safe Handling:	The product is intended for professional use. Leaflet M044, production and processing of Polyurethanes and isocyanate. Please note the current safety data sheets.
VOC-Content:	VOC-directive 2004/42/EG: Category IIA/j type Ib < 500 g/l VOC
Disposal:	Disposal with the assistance of a disposal specialist under consideration of the current safety data sheets.
GISCODE:	PU 10

Data base:

The determination of all the data and application information is based in laboratory tests. Measured values in practice may differ because of influences beyond our control.

Legal foundation:

The following specifications as well as the recommendations for handling and use of our products are based upon our knowledge and experience under normal conditions, at proper storing and application. Because of different materials, substrates and working conditions other than given normal values, a warranty of a working result or a liability – for whatever legal relationship - cannot be justified from these instructions or a verbal guidance respectively, unless intent or gross fault can be imputed to us. Here, the user has to prove that he had transferred in written form, in time and completely every knowledge that is necessary for an appropriate and promising estimation. The user is obliged to test the products on their suitability for the intended purpose. Incidentally our respective terms and conditions of business are valid. You get these on www.gremmler.de. Only the newest edition of this technical data sheet is valid.